
# DURACELL®

## CR2032

### Lithium/Manganese Dioxide Battery





#### **Key Features**

- High voltage response, stable during most of the lifetime of the application
- Reliable Performance
- Child-Safe Markings & Retail Packaging
- Wide operating temperature range (-20°C/+60°C)
- Low self-discharge with long operating life (<2% after 1 year of storage at + 20 °C)</li>
- Excellent resistance to corrosion
- Designed to meet all major quality, safety and environment standards:
  - o Safety: IEC 60086-4
  - o Transport: UN 38.3
  - $\circ~$  RoHS and REACH compliance
  - Quality: ISO 9001, Duracell World Class Continuous Program



Berkshire Corporate Park Bethel, CT. 06801 U.S.A. Telephone: Toll-free 1-800-544-5454 www.duracell.com

#### **Electrical characteristics**

| • | Nominal capacity (15k Ohm Cont., 2.0 V cut-off) | 225 mAh |
|---|---|---------|
| • | Open circuit voltage (at + 20 °C)               | 3.0 V   |
| • | Minimum Load Voltage (150 Ohm @ 0.5 sec)        | 2.1V    |
| - | Standard Continuous Discharge Current           | 0.2 mA  |
| • | Maximum Continuous Discharge Current            | 3 mA    |
| • | Maximum Pulse Discharge Current at 1 sec        | 10 mA   |
| • | Nominal Energy                                  | 657 mWh |
| - | AC Impedance @ 1kHz                             | 20 Ohm  |

#### Physical characteristics

| Typical weight   |  |  |
|------------------|--|--|
| Li metal content |  |  |
| Battery Case     |  |  |

3.03 g (0.11 oz.) approx. 0.07 g Ni Plated Steel

Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

CR2032PGOE M0620

# DURACELL®

## CR2032

### Lithium/Manganese Dioxide Battery


#### **Typical applications**


- Medical devices
- Security devices
- Fitness devices
- Watches
- Calculators
- Wireless sensors
- Toys
- Key-Fobs & Trackers


#### **Operating conditions**

| <ul> <li>Operating temperature range</li> </ul>               | -20°C to 60°C<br>(14°F to 140°F) |
|---|----------------------------------|
| <ul> <li>Storage temperatures</li> <li>Recommended</li> </ul> | 5°C to 30°C<br>(41°F to 86° F)   |

Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.








Pulse Testing 270/1300 Ohm, 5m/h to 2.OV 3.5 3 2.5 Voltage 1.5 0.5 0 **–** 37.5 40 42.5 45 5 47.5 Service Hrs 52.5 55 57.5 50

CR2032PGOE M0620

# DURACELL®

### CR2032

Lithium/Manganese Dioxide Battery



#### 60086-4 © IEC:2007 Edition 3.0

| Test | Test designation       | Observation |
|------|------------------------|-------------|
| А    | Altitude               | Pass        |
| В    | Thermal cycling        | Pass        |
| С    | Vibration              | Pass        |
| D    | Shock                  | Pass        |
| E    | External short circuit | Pass        |
| F    | Impact                 | Pass        |
| G    | Crush                  | Pass        |
| Н    | Forced discharge       | Pass        |
| I    | Abnormal charging      | Pass        |
| J    | Free fall              | Pass        |
| К    | Thermal Abuse          | Pass        |

#### Warning

Fire, explosion and burn hazard Do not recharge, short circuit, crush, disassemble, heat above 100  $^{\circ}$ C (212  $^{\circ}$ F), incinerate, or expose contents to water

#### Warning! Keep batteries away from children!

Always keep your batteries away from children to prevent swallowing. If ingestion does occur, however, be aware that initial symptoms may be similar to other childhood illnesses such as coughing, drooling and discomfort.

#### Storage

The storage area should be clean, cool (preferably not exceeding +30  $^\circ$ C), dry and ventilated



Berkshire Corporate Park Bethel, CT. 06801 U.S.A. Telephone: Toll-free 1-800-544-5454 www.duracell.com Delivered capacity is dependent on the applied load, operating temperature and cut-off voltage. Please refer to the charts and discharge data shown for examples of the energy/service life that the battery will provide for various load conditions.

CR2032PGOE M0620